



湖北迈尔斯石化有限公司

Hubei Myers Petrochemical Co., Ltd.

Fisher Tropsch Wax

Testing Method	Specification	Method
PHYSICAL STATE(25℃)	Solid	
COLOUR	White	VISUAL
CONGEALING POINT	93-96(℃)	ASTM D-938
DROP MELTING POINT	105-109(℃)	ASTM D-127
SOFTENING POINT	101-106(℃)	ASTM D-36
NEEDLE PENETRATION 25℃	2.5(dmm)Max	ASTM D1321
NEEDLE PENETRATION 43℃	7(dmm)Max	ASTM D1321
VISCOSITY 140℃	30(cPs/mPas)Max	ASTM D3236

Address: 517-2-3; Lianchang Road ,Duodao District, Jingmen City, Hubei province, China

Telephone & fax: 0724-2218611

Website: <http://hberic.com/English/>